

WEEDGUARD™
landscaping geotextile

T: +44 (0)1621 874200
F: +44 (0)1621 874299

Product Data Sheet

Issue: 03 Date: 12.09.12 Page: 1 of 2

Fibre composition

Polypropylene core (70%)/polyethylene sheath (30%)

Mechanical Properties (Mean values)

Tensile Strength	EN ISO 10319	kN/m	6.0
Elongation	EN ISO 10319	%	28
CBR Puncture Resistance	EN ISO 12236	N	800

Hydraulic Properties (Mean values)

Permeability	EN ISO 11058	l/m ² .s	105
Opening Size	EN ISO 12956	μm	160

Physical Properties (Typical values)

Mass per unit area ₍₂₎	EN ISO 9864	g/m ²	90
Thickness	EN 964-1	mm	0.68

Durability

This product is predicted to be durable for more than 25 years in soils with a pH in the range 2 to 14 and with a temperature of less than 25°C.

Chemical resistance

Polypropylene and polyethylene are unaffected by the chemicals which normally exist in soils.

Biological resistance

Polypropylene and polyethylene are not nutrients for micro-organisms and do not provide nourishment for animals & insects.

UV exposure

Fiberweb Geosynthetics' products are delivered to site in polyethylene wrapping to protect against the effects of ultra-violet radiation. It is recommended that the products remain wrapped until their installation.

Once unwrapped, the products should be completely covered with fill within 14 days to avoid exposure to UV radiation.

Versions of most products can be manufactured with enhanced UV performance by incorporating stabilisers. These versions carry the suffix UV.

The remaining properties are identical to the corresponding standard grade.

Adequate precautions should always be taken to protect all products from UV radiation to achieve the stated durability.

Notes:

1. Refer to the *Terram Jointing Methods* (downloadable from www.terram.com) for when simple overlaps are required for subsequent and adjacent roll lengths. However, pegging, sewing, stapling or gluing can also be used depending upon the application, the sub-grade conditions, the loading, the convenience and the cost.
2. These figures relate to standard product weights and roll sizes. Other weights, sizes and colours may be available on request. For further information please contact Fiberweb Geosynthetics' Technical Support.

As part of its continual improvement process Fiberweb Geosynthetics Ltd reserve the right to change the properties listed on this data sheet without prior notice.

TM indicates a trade mark of Fiberweb plc or a Fiberweb Group company, many of which are registered in a number of countries around the world.